

PRODUCT DATA SHEET

Sika® Watertight Concrete Powder

Water Resisting Concrete Admixture



PRODUCT DESCRIPTION

Sika® Watertight Concrete Powder is a combined water resisting and HRWR/Superplasticising admixture, used to enhance the workability of and reduce the water permeability of concrete.

The product incorporates Sika® ViscoCrete Superplasticiser Technology and, depending on the material package, can produce watertight concrete at an S3 consistence with a w/c ratio of <0.45 without the addition of a separate HRWR/Superplasticiser.

Watertight concrete can be produced which is suitable for BS8102:2009 Type B construction (grades 1-3).

USES

Sika® Watertight Concrete Powder has been specifically formulated to produce high quality watertight concrete.

Sika® Watertight Concrete Powder is used as a constituent of the Sika® Watertight concrete system and contact MUST be made with Sika Ltd to ensure that full system compliance is achieved. This Technical Data Sheet MUST be read in conjunction with Sika publication Sika® Solutions for Watertight Concrete.

Typical Applications:

- Water retaining structures
- Below ground structures
- Swimming pools
- Lift pits
- Tunnels

CHARACTERISTICS / ADVANTAGES

- Reduced water absorption
- Reduced water penetration
- Accurate control of w/c ratio
- In combination with a Sika® ViscoCrete HRWR/Superplasticiser, SCC can be produced
- Reduced shrinkage and creep
- Provided in a water soluble bag for ease of dispensing
- Consistent performance
- Reduced stock and environmental issues at production plant

APPROVALS / STANDARDS

Conforms to the requirements of BS EN 934-2 Table 9 DoP 43202223, certified by Factory Production Control Body 1029 and provided with the CE mark
DoP 16990478, certified by Factory Production Control Body 0120 and provided with the UKCA mark
BBA Agrément Certificate 08/4606

PRODUCT INFORMATION

Chemical Base	Combination Fatty Acid and Polycarboxylate
Packaging	6 x 1.75 kg bags (1 pail)
Appearance / Colour	White powder
Shelf Life	12 months from date of production if stored in unopened and undamaged original sealed containers.
Storage Conditions	Protect from moisture, store at temperatures between +5°C and +25°C.
Bulk Density	0.50 kg/lt
Total Chloride Ion Content	< 0.1 % w/w (chloride free)
Equivalent Sodium Oxide	< 0.4% w/w (alkali content)
Compatibility	<p>Sika® Admixtures:</p> <ul style="list-style-type: none">▪ Compatible with all ViscoCrete®, ViscoFlow®, Sikament® and Plastiment® Plasticisers/Superplasticisers▪ Other product compatibility information available on request <p>Cements:</p> <ul style="list-style-type: none">▪ All cement combinations <p>If used in combination with a Sika® admixtures in the construction of a watertight environment, contact MUST be made with Sika Ltd</p>
Dispensing	<ul style="list-style-type: none">▪ Forced action and truck mixers should be free from all contaminants prior to the batching of concrete containing Sika® Watertight Concrete Powder.▪ Sika® Watertight Concrete Powder should be added to the mixer at the recommended dose (1 bag per m³) prior to the batching of concrete.▪ Batched concrete mix constituents should be subsequently batched on to the Sika® Watertight Concrete Powder in accordance with Sika® mix design recommendations.▪ Additional mixing water should then be dispensed to bring the concrete to the desired consistence.▪ On completion of the batching procedure the concrete load should be mixed in the truck mixer/agitator on full revolutions for a minimum of 5 minutes to ensure that the optimum consistence has been achieved.▪ The w/c ratio and consistence control remains the responsibility of the concrete producer. Laboratory trials are recommended to evaluate and confirm the actual water reduction.
Restrictions	<ul style="list-style-type: none">▪ In the event of part loads < 1.0 m³ it is recommended that a 1 m³ dose of Sika® Watertight Concrete Powder is used

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet
Sika® Watertight Concrete Powder
October 2021, Version 02.03
021403011000000109

SikaWatertightConcretePowder-en-GB-(10-2021)-2-3.pdf